

MADISON COUNTY HIGHWAYS

1.57

NO. <b>48</b>	SECTION (S)	NAME <del>Goodson</del> <b>BYERLEY &amp; GOODSON</b>
<b>Twp. Road.</b>	FROM <b>Junction C-14 (Taylor-Blair)</b>	TO <del>Junction F-137 (Byerley Mill)</del> <b>S.R. #47</b>
	LENGTH <del>8078</del> <b>8290</b>	(IN FEET) MILES <b>1.57</b>
	PAVEMENT TYPE <b>Gravel</b>	WIDTH <b>15</b>
	WIDTH OF R OF W <b>40</b>	WIDTH OF BERMS <b>2</b>
	FEEET <del>8078</del>	FEEET
	TWP. <b>Jefferson</b> MILES <b>1.57</b>	TWP. MILES TWP. MILES
	REMARKS <b>TOWNSHIP ROAD</b>	

HISTORY

PETITIONED	ROAD RECORD BOOK	COMM. VOL.	JOURNAL PAGE	REMARKS
	<b>RR#1</b>		<b>87</b>	<b>Laid out 1846 S. J. Coons Rd.</b>

IMPROVEMENTS

YEAR	TYPE OF	APPLIED BY	REMARKS
<b>1957</b>	<b>Beam Bridge</b>	<b>County</b>	<b>New bridge erected by Co forces</b>
<b>1962</b>		<b>"</b>	<b>Sidges removed by Twp.</b>

## IMPROVEMENTS Cont.

48 1.517

YEAR	TYPE OF	APPLIED BY	REMARKS
1962		County	Berms & ditches cut and road widened new pipe culverts, catch basin at bottom of still with 128' of 21" laid in ditch. Some stone applied
1963	Black top	County	Road bed built up to 7" primed and sealed with #46 stone
1964	TAR #6 STONE		SURFACE TREATED
1967	TAR #6 STONE	COUNTY	SURFACE TREATED
1970	TAR #6 STONE	COUNTY	SURFACE TREATED
1973	RS2S #8 stone	County	Surface treated
1976	5,127 Gal. RS2	COUNTY	183.45 ton #8 limestone - 4.0
1980	206.70 tons #8 7,038 Gal. RS2	County W.K.W.	Surface treated
1984	210.7 TON #8 6,099 gals. RS2	Koch-W.K.W.	Surface Treated
1987	280.10 TONS #8 6,000 GAL. RS2	COUNTY CENTRAL OIL	SURFACE TREATED
1990	7484.33 gal. liquid asphalt 262 tons #8	County	Surface treated
1997	402 asphalt	Northwood	Pave 1123.97 Tons 1.25" Lift
	404		643.85    .75" Lift
	304 Limestone		Berm 330.23